




SILOXTREME



| <u>PROPERTIES</u> | <u>VALUE</u> | <u>UNITS</u> | <u>STANDARD</u> |
|--|-------------------|--------------|-----------------|
| Thickness | 115/125 (*) | μ | ISO 4591 |
| <u>MECHANICAL PROPERTIES</u> | | | |
| Tensile strength at break | | | |
| M.D. | 25 | MPa | EN ISO 527 |
| T.D. | 23 | MPa | EN ISO 527 |
| Elongation at break | | | |
| M.D. | 600 | % | EN ISO 527 |
| T.D. | 800 | % | EN ISO 527 |
| Impact Resistance F50 | | | |
| FLAT | >600 | gr | ISO 7765 |
| FOLD | 300 | gr | ISO 7765 |
| <u>OPTICAL PROPERTIES</u> | | | |
| Relative light transmission | <10 ⁻³ | % | EN 2155 |
| Film reflexion W/B  | >65 | % | EN 2155 |
| <u>AGEING PROPERTIES</u> | | | |
| Agricultural seasons | 18 | Months (**) | |

(*) Properties made on a 125 microns film.

(**) Duration in areas with radiation of 130 Kly/year. For different conditions, contact SOLPLAST S.A.



All the data contained in this Specification Sheet has been obtained through our own experience and is offered at an informative level. They are obtained under optimal process conditions and therefore may vary depending on product dimensions, extruding equipment, etc. SOLPLAST reserves the right to change these data at any time without notice. These data are given with all the goodwill but as the circumstances and conditions upon which this information could be used are beyond our control, we cannot accept any responsibility for any lost or damage caused by its use.

For any other option consult with us at info@solplast.com