




SILOFARM



<u>PROPERTIES</u>	<u>VALUE</u>	<u>UNITS</u>	<u>STANDARD</u>
Thickness	150/200 ^(*)	μ	ISO 4591
<u>MECHANICAL PROPERTIES</u>			
Tensile strength at break			
M.D.	21	MPa	EN ISO 527
T.D.	19	MPa	EN ISO 527
Elongation at break			
M.D.	450	%	EN ISO 527
T.D.	650	%	EN ISO 527
Impact Resistance F50			
FLAT	325	gr	ISO 7765
FOLD	150	gr	ISO 7765
<u>OPTICAL PROPERTIES</u>			
Relative light transmission	<10 ⁻³	%	EN 2155
Film reflexion W/B 	>50	%	EN 2155
<u>AGEING PROPERTIES</u>			
Agricultural seasons	12	Months ^(**)	

(*) Properties made on a 150 microns film.

(**) Duration in areas with radiation of 130 Kly/year. For different conditions, contact SOLPLAST S.A.



All the data contained in this Specification Sheet has been obtained through our own experience and is offered at an informative level. They are obtained under optimal process conditions and therefore may vary depending on product dimensions, extruding equipment, etc. SOLPLAST reserves the right to change these data at any time without notice. These data are given with all the goodwill but as the circumstances and conditions upon which this information could be used are beyond our control, we cannot accept any responsibility for any lost or damage caused by its use.

For any other option consult with us at info@solplast.com