



OXYSEAL



PROPERTIES

VALUE

UNITS

STANDARD

Thickness

90

μ

ISO 4591

MECHANICAL PROPERTIES

Tensile strength at break

M.D.

38

MPa

EN ISO 527

T.D.

41

MPa

EN ISO 527

Elongation at break

M.D.

600

%

EN ISO 527

T.D.

600

%

EN ISO 527

Impact Resistance F50

FLAT

600

gr

ISO 7765

FOLD

300

gr

ISO 7765

SPECIAL PROPERTIES

O₂ permeability

<2

Cc/m² día
23°C 0% RH



All the data contained in this Specification Sheet has been obtained through our own experience and is offered at an informative level. They are obtained under optimal process conditions and therefore may vary depending on product dimensions, extruding equipment, etc. SOLPLAST reserves the right to change these data at any time without notice. These data are given with all the goodwill but as the circumstances and conditions upon which this information could be used are beyond our control, we cannot accept any responsibility for any lost or damage caused by its use.

For any other option consult with us at info@solplast.com