



SHRINK WRAP FILM FOR CUCUMBERS



PROPERTIES

VALUE

UNITS

STANDARD

Thickness

15

μ

ISO 4591

MECHANICAL PROPERTIES

Tensile strength at break

M.D.

22

MPa

EN ISO 527

T.D.

15

MPa

EN ISO 527

Elongation at break

M.D.

300

%

EN ISO 527

T.D.

400

%

EN ISO 527

Tear resistance

D.M.

5.000

Gr/mm

EN 13206

D.T.

9.000

Gr/mm

EN13206

Impact Resistance F50

FLAT

50

gr

ISO 7765

SPECIAL PROPERTIES

- Microperforated film.



All the data contained in this Specification Sheet has been obtained through our own experience and is offered at an informative level. They are obtained under optimal process conditions and therefore may vary depending on product dimensions, extruding equipment, etc. SOLPLAST reserves the right to change these data at any time without notice. These data are given with all the goodwill but as the circumstances and conditions upon which this information could be used are beyond our control, we cannot accept any responsibility for any lost or damage caused by its use.

For any other option consult with us at info@solplast.com