

PRODUCTS  
**DISINFECTION BY  
 BIOFUMIGATION**



**SOLTIF BF**



<u>PROPERTIES</u>	<u>VALUE</u>	<u>UNITS</u>	<u>STANDARD</u>
<b><u>MECHANICAL PROPERTIES</u></b>			
<b>Tensile strength at break</b>			
M.D.	35	MPa	EN ISO 527
T.D.	35	MPa	EN ISO 527
<b>Elongation at break</b>			
M.D.	500	%	EN ISO 527
T.D.	600	%	EN ISO 527
<b>Yield strength</b>			
M.D.	15	Mpa	EN 13206
T.D.	15	Mpa	EN 13206
<b>Dart-test F50</b>			
FOLD	150	gr	ISO 7765
<b><u>OPTICAL PROPERTIES</u></b>			
Global light transmission	91	%	EN 2155
Thermicity	60	%	EN 13206

**AGEING PROPERTIES**

**Agricultural seasons** 1 Season (\*)

**SPECIAL PROPERTIES:**

- High barrier to gases released in the decomposition of organic matter.
- O<sub>2</sub> permeability <4 cm<sup>3</sup>/m<sup>2</sup> day.
- Anti-drip effect.
- Thermal effect.

(\*) Duration in areas with radiation of 150 kly / year. For different conditions, contact SOLPLAST, S.A.



All the data contained in this Specification Sheet has been obtained through our own experience and is offered at an informative level. They are obtained under optimal process conditions and therefore may vary depending on product dimensions, extruding equipment, etc. SOLPLAST reserves the right to change these data at any time without notice. These data are given with all the goodwill but as the circumstances and conditions upon which this information could be used are beyond our control, we cannot accept any responsibility for any lost or damage caused by its use.

For any other option consult with us in the email [info@solplast.com](mailto:info@solplast.com)